

Rapid Set[®]

PROFESSIONAL GRADE

Construction Cement Products

MORTAR MIX

HIGH STRENGTH REPAIR MORTAR

— FOR CONCRETE REPAIR & ONE-COAT STUCCO —

FAST

Sets in 15 Minutes,
Rock Solid in 1 Hour

STRONG

300% stronger than
most mortar

DURABLE

Formulated for Permanent Life.
Non-Shrink, Crack Resistant



Available in 55-lb and 25-lb sizes

STUCCO REPAIR



CONCRETE REPAIR



WALL REPAIR



APPROVED

ASTM C928
ICBO 1157

www.rapidset.com

MORTAR MIX

HIGH STRENGTH REPAIR MORTAR

FOR CONCRETE REPAIR & ONE-COAT STUCCO

Rapid Set®

Construction Cement Products

1. Product Name:**Rapid Set® Mortar Mix**
High Strength Mortar**2. Manufacturer:**CTS Cement Manufacturing Corp.
11065 Knott Ave., Suite A
Cypress, CA 90630
Ph. 800-929-3030
Fx. 714-379-8270
Web: www.rapidset.com
E-mail: info@rapidset.com**3. Product Description:**

When mixed with water MORTAR MIX produces a workable, high quality mortar that is ideal where rapid strength gain, high durability and low shrinkage are desired. Apply MORTAR MIX in thicknesses from 1/2-in to 6-in. Durable in wet environments. **SETS IN 15 MINUTES & IS READY FOR TRAFFIC IN 1-HOUR.** One 55 lb. bag of Rapid Set® MORTAR MIX will yield approximately 0.5 cubic feet.

Uses:

MORTAR MIX is a versatile product that can be used for general concrete repair, stucco & plaster repair, one-coat exterior plaster, mortar beds, underlayments, and formed work. MORTAR MIX is suitable for vertical and overhead applications.

Composition:

Rapid Set® MORTAR MIX is a high performance blend of Rapid Set® hydraulic cement and quality sand. MORTAR MIX is non-metallic and no chlorides are added. Rapid Set® MORTAR MIX is similar in appearance to portland cement based mortars and may be applied using similar methods.

Color: [Light Grey]

The final color of MORTAR MIX may vary due to application techniques and environmental conditions.

Limitations:

Not intended for applications over 6" deep, for deeper sections use Rapid Set® Concrete Mix. For overlay applications at least one test section should be prepared to evaluate the suitability of the materials and procedures.

4. Technical Data:**a. Set Time**ASTM C-191 (Mod.) at 70°F
Initial Set 15-minutes
Final Set 35-minutes**b. Compressive Strength**

ASTM C-109 Mod.

Age	Compressive Strength
1-hour*	2500-psi
3-hour	4000-psi
7-day	5000-psi
28-day	7000-psi

c. Slant Shear

ASTM C-882 Mod.

1-day	1000-psi
28-day	2200-psi

* After final set.

5. Using MORTAR MIX**Surface Preparation:**

For repairs, adjacent surfaces shall be clean, sound and free from any materials that may inhibit bond such as oil, asphalt, curing compounds, acids, dirt and loose debris. Roughen surface and remove all unsound material. Immediately prior to placement the repair surface shall be thoroughly saturated with no standing water.

Mixing:

The use of a power driven mechanical mixer, such as a mortar mixer or a drill mounted mixer, is recommended. Organize work so that all personnel and equipment are in place before mixing. Use clean Potable water. Rapid Set® MORTAR MIX may be mixed using 3 to 5 quarts of water per 55 lb. bag. Use less water to achieve higher strengths. DO NOT exceed 5 quarts of water per bag. For increased fluidity and workability use Rapid Set® FLOW CONTROL® plasticizing admixture from the Concrete Pharmacy®. Place the desired quantity of mix water into the mixing container. While the mixer is running add Rapid Set® MORTAR MIX. Mix for the minimum amount of time required to achieve a lump-free, uniform consistency (usually 1 to 3 minutes). Do not re-temper.

Placement:

Rapid Set® MORTAR MIX may be placed using traditional methods. Organize work so that all personnel and equipment are ready before placement. Place, consolidate and screed quickly to allow for maximum finishing time. Do not wait for bleed water, apply final finish as soon as possible. Rapid Set® MORTAR MIX may be troweled, floated or texture finished. On flat work do not install in layers, install full depth sections and progress horizontally. Do not install on frozen surfaces. Use a method of

consolidation that eliminates air voids. To extend working time use Rapid Set® SET CONTROL® set retarding admixture.

Curing: Water cure all Rapid Set® MORTAR MIX installations. Begin curing as soon as the surface has lost its moist sheen. Keep exposed surfaces wet for a minimum of 1 hour. When experiencing extended setting times, due to cold temperature or the use of retarder, longer cure times may be required. The objective of water curing shall be to maintain a continuously wet surface until the product has achieved sufficient strength.

Temperature:

Warm environmental and materials temperatures will reduce the working time of MORTAR MIX. To compensate for warm temperatures, keep material cool and use chilled mix water. Temperatures below 70°F (21°C) will decrease the rate of strength gain and MORTAR MIX should not be applied if surface or ambient temperature is below 45°F (7.2°C).

6. Limited Warranty:

CTS Cement Manufacturing Corporation warrants its material to be of good quality, and, at its sole option, within one year from date of sale, will replace defective materials or refund the purchase price thereof and such replacement or refund shall be the limit of CTS's responsibility. Except for the foregoing, all warranties, express or implied including merchantability and fitness for a particular purpose are excluded. CTS shall not be liable for any consequential, incidental, or special damages arising directly or indirectly from the use of the material.

7. Caution:

MORTAR MIX contains cementitious materials and may cause irritation to lungs, eyes and skin. Avoid contact. Use only in adequate ventilation. Do not breath dust. Wet mixture may cause burns. Wear suitable gloves, eye protection and protective clothing. In case of skin contact, wash thoroughly with soap and water. In case of eye contact, flush immediately and repeatedly with large quantities of water and get prompt medical attention. In case of difficulty breathing, remove person to fresh air. If difficulty breathing persists, seek medical attention.